



DECLARATION OF PERFORMANCE

No. DoP LO-UK-L-SM-2/08-CPR-23-1

according to Annex III of the Regulation (EU) No 305/2011 of the European Parliament and Construction Products Regulation 2011 (retained EU law EUR 305/2011) as amended by the Construction Products (Amendment etc) (EU Exit) Regulations 2019 and the Construction Products (Amendment etc) (EU Exit) Regulations 2020

UNIQUE IDENTIFICATION CODE OF THE PRODUCT – TYPE:	
Long hot rolled products of structural steels non-alloy structural steels steel grade S355J0 (1.0553)	
<ul style="list-style-type: none">- IPN/IPE beams 80 - 220- IPE A/IPE AA beams 80 - 220- UPN channels 50 - 220 mm- Equal angles L 35 - 150, thickness 3 - 18 mm- Unequal angles L 100x65 up to 140x90, thickness 7 - 14 mm- Round bars \varnothing 10 - 110 mm- Square bars 14 - 16 mm- HE 100 A/B – HE 140 A/B wide flange beams- Flat bars width 18 - 180 mm, and flat bars of thickness 10 - 25 mm and width 200 mm	
INTENDED USE:	Metal structures or mixed metal and concrete structures
MANUFACTURER:	LIBERTY OSTRAVA a.s. Vratimovská 689/117, Kunčice 719 00 Ostrava Czech Republic Tel. +420 59 733 1111 https://libertysteelgroup.com/cz
SYSTEM/S OF AVCP:	System 2+
HARMONISED / DESIGNATED STANDARD:	EN 10025-1:2004
NOTIFIED BODY (EU):	Technický a zkušební ústav stavební Praha, s.p. Prosecká 811/76y, Praha 9 – Prosek No. 1020
APPROVED BODY (UK):	TUV UK Limited AMP House Suites 27 – 29 Fifth Floor Dingwall Road Croydon CR0 2LX No. 0879

DECLARED PERFORMANCES:

Essential characteristic		Performance		Harmonised / Designated technical specification
Tolerances on dimensions and shape	Angles		EN 10056-1, 2	
	IPN and H sections		EN 10365, EN 10034	
	Tapered Flange IPE		EN 10365, EN 10024	
	UPE, UPN		EN 10365, EN 10279	
	Flat / Square / Round bars		EN 10058/EN 10059/EN 10060	
Yield strength	Nominal thickness(mm)		Values (MPa)	
	>	≤	min	
		16	355	
	16	40	345	
	40	63	335	
	63	80	325	
	80	100	315	
Tensile strength	Nominal thickness(mm)		Values (MPa)	
	>	≤	min	max
	=3	100	470	630
	100	140	450	600
Elongation	Nominal thickness(mm)		Values (%)	
	>	≤	min	
	=3	40	22	
	40	63	21	
	63	100	20	
Impact strength	Nominal thickness(mm)		Values (J)	
	>	≤	min	
		140	27 at 0°C	
Weldability (CEV)	Nominal thickness(mm)		Values (%)	
	>	≤	max	
		30	0,45	
	30	40	0,47	
Durability (Chemical composition)	Nominal thickness(mm)		Values (%)	
	>	≤	max	
		140	C*: 0,20	Cu: 0,55
			Si: 0,55	S: 0,035
			Mn: 1,60	N**: 0,012
			P: 0,035	
* For Nominal thickness> 30 mm C: 0,22. For Nominal thickness>100 mm: C content upon agreement				
** The max. value for nitrogen does not apply if the chemical composition shows a minimum total Al content of 0,020% or if sufficient other N binding elements are present				

EN 10025-1:2004

This declaration of performance is issued, in accordance with Regulation (EU) No 305/2011, as it has effect in the United Kingdom, under the sole responsibility of the manufacturer identified above.

Signed for and on behalf of the manufacturer by:

David Božon

At Ostrava, on 12th of January 2023

The Declarations of Performance for download: <https://libertysteelgroup.com/cz>