## **Declaration of Performance**

(according to regulation EU No 305/2011)

## No. Plate **\$275J2**

## Plate S275J2 / 1.0145 according EN 10025-2

To be used in Metal Structures and Composite Metal and Concrete Structures

## Liberty Steel Dalzell Limited

Park Street, Motherwell, ML1 1PU United Kingdom Tel: +44 (0)1698 266100 Website: www.libertyhg.com/Dalzell

CE Marking Notified Body Lloyds Register Verification Limited 71 Fenchurch Street, London, EC3M 4BS Tel: +44 (0)207 423 2428 Email: ecdirectives@lr.org Website: www.lr.org

System of assessment and verification of constancy of performance of the product System 2+

Notified factory production control certification body No. 0038 performed the initial inspection of the manufacturing plant and of factory production control and the continuous surveillance, assessment, and evaluation of factory production control and issued the certificate of conformity of the factory production control



Jon Bolton CEO Liberty Steel Dalzell Limited Date: 15<sup>th</sup> September 2016

Essential Characteristic	Performance				Harmonised Technical Specification
Tolerances on dimensions & shape	Thickness		EN 10029		
	Flatness		EN 10029		
	Nominal Thickness (mm)		Values Min (Mpa)		
	>	<=			
	-	16	275		
Yield strength	16	40	265		
(transverse)	40	63	255		
	63	80	245		
	80	100	235		
	100	150	225		
	Nominal Thick		) Values (Mpa)		
Tensile strength	>	<=	Min	Max	
(transverse)	5	100	410	560	
	100	150	400	540	
Elongation (transverse)	Nominal Thickness (mm)		Values Min (%, 5.65√so)		
	>	<=	Values Will (70, 5.05 (50)		EN10025-1 2004
	5	40	21		
	40	63	20		
	63	100	19		
	100	150	19		
Impact strength (longitudinal)	J2		27J at - 20°C		
Weldability CEV	Nominal Thickness (mm)		Values Max (%)		
	>	<=	Values Max (%)		
	-	40	0.40		
	40	150	0.42		
Durability	Nominal Thickness (mm)		Values Max (%)		
	-	150	C: 0.18		
			Mn: 1.50		
			P: 0.025		
			S: 0.025		
			Cu: 0.55		

CE 0038 Liberty Steel Dalzell Limited Park Street, Motherwell, ML1 1PU United Kingdom 16 Plate S275J2 EN 10025-1-2004 Plate S275J2 / 1.0145 To be used in Metal Structures and Composite Metal and Concrete Structures Tolerances on dimensions: Plate EN10029 Elongation: Tensile Strength: Yield Strength: EN10025-2 Impact Strength: Weldability: Durability: Dangerous Substances: No Performance Determined