Declaration of Performance

(according to Construction Product Regulation (EU Exit) 2020 No 1359)

No. Plate \$275J0

Plate **S275J0 / 1.0143** according **EN 10025-2**

To be used in Metal Structures and Composite Metal and Concrete Structures

Liberty Steel Dalzell Limited

Park Street, Motherwell, ML1 1PU United Kingdom

Tel: +44 (0)1698 266100

Website: https://libertysteelgroup.com/uk/our-locations/liberty-steel-dalzell/

UK Conformity Assessment Body LRQA Verification Limited, 1 Trinity Park Bickenhill Lane, Birmingham B37 7ES Tel: +44 (0)330 414 1351 Website: www.lrqa.com

System of assessment and verification of constancy of performance of the product

System 2+

Factory production control assessment body No. 0038 performed the initial inspection of the manufacturing plant and of factory production control and the continuous surveillance, assessment, and evaluation of factory production control and issued the certificate of conformity of the factory production control

Signed for and behalf of Liberty Steel Dalzell Ltd;

Name: Kenny McLeary Title: Technical Manager

Sign: K McLeary
Date: 04/02/22



Essential Characteristic	Performance				Harmonised Technical Specification
Tolerances on	Thickness		EN 10029		
dimensions & shape	Flatness		EN 10029		
Yield strength (transverse)	Nominal Thickness (mm)		Values Min (Mpa)		
	>	<=	values will (wpa)		
	-	16	275		
	16	40	265		
	40	63	255		
	63	80	245		
	80	100	235		
	100	150	225		
Tensile strength (transverse)	Nominal Thic	ckness (mm)	Values (Mpa)		
	>	<=	Min	Max	
	5	100	410	560	
	100	150	400	540	
Elongation (transverse)	Nominal Thickness (mm)		Value Min	(% 5.65)co)	
	>	<=	Values Min (%, 5.65√so)		
	5	40	21		EN10025-1 2004
	40	63	20		
	63	100	19		
	100	150	19		
Impact strength (longitudinal)	J0		27J at 0°C		
Weldability CEV	Nominal Thickness (mm)		Values May (9/)		
	>	<=	Values Max (%)		
	-	40	0.40		
	40	150	0.42		
Durability	Nominal Thickness (mm)		Values Max (%)		
	-	150	C: 0.18		
			Mn: 1.50		
			P: 0.030		
			S: 0.030		
			N: 0.012		
			Cu: 0.55		



Liberty Steel Dalzell Limited Park Street, Motherwell, ML1 1PU United Kingdom

16

Plate S275J0

EN 10025-1 - 2004

Plate **S275J0 / 1.0143**

To be used in Metal Structures and Composite Metal and Concrete Structures

Tolerances on dimensions: Plate EN10029

Elongation: Tensile Strength:

Yield Strength: EN10025-2

Impact Strength: Weldability: Durability:

Dangerous Substances: No Performance Determined