

DECLARATION OF PERFORMANCE
according to regulation (EU) No. 305/2011

No. LO-F-ST-2/12-CPR-22-1

Unique identification code of the product-type:

Hot rolled strip, band and sheet of structural non-alloy steels grade S235JRC according to EN 10025-2, steel number 1.0122

Intended use: Metal structures or in composite metal and concrete structures.

Manufacturer :
LIBERTY Ostrava a.s.
Vratimovská 689/117
719 00 Ostrava – Kunčice
Czech Republic
Tel. +420 59 733 1111
libertysteelgroup.com/cz

System of AVCP: System 2+


Harmonised standard: EN 10025-1:2004

Notified body:
Technický a zkušební ústav stavební Praha, s.p.
Prosecká 811/76a, Praha 9 – Prosek,
NB No. 1020

The performance of the product identified above is in conformity with the set of declared performances. This declaration of performance is issued, in accordance with Regulation (EU) No 305/2011, under the sole responsibility of the manufacturer identified above.

Signed for and on behalf of the manufacturer by:

At Ostrava on 1.4.2022


Ing. Jan Pudich
Director of Plant 16 – Downstream Flat

Declared performances				
Basic characteristics	Performance			Harmonised technical specification
Dimensional tolerance	Sheets, strips, stripes		EN 10051	
Yield point (Re)	Nominal thickness (mm)		Values (Mpa)	
	>	≤	min	
		16	235	
Ultimate tensile strength (Rm)	Nominal thickness (mm)		Values (Mpa)	
	>	≤	min	max
		100	360	510
Elongation**	Nominal thickness (mm)		Values (%)	
	>	≤	min. T	min. L
	1	1.5	16	18
	1.5	2	17	19
	2	2.5	18	20
	> 2.5	<3	19	21
	≥3	≤40	24	26
Impact energy	Nominal thickness (mm)		Values (J)	
	>	≤	min	
		150	27 at 20°C	
Weldability CEV	Nominal thickness (mm)		Values (%)	
	>	≤	max	
		30	0.35	
Chemical composition	Nominal thickness (mm)		Values (%)	
	>	≤		
		16	C: 0.17	Cu: 0.55
			Mn: 1.40	N*: 0.012
			P: 0.035	
			S: 0.035	
			* The maximum nitrogen content values do not apply if the total Al content is at least 0.020%, or if other adequate elements that bind N are present.	
		** Elongation, T – transversal direction, L – Longitudinal direction		

EN 10025-1:2004